

The listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims:

1. (Previously Presented) Surface-modified effect pigments based on flake-form substrates, which are sheathed with one or more layers of immobilised LCST and/or UCST polymer, wherein said surface-modified effect pigments based on flake-form substrates are holographic pigments, pearlescent pigments, interference pigments, multilayered pigments, metal-effect pigments, goniochromatic pigments and/or BiOCl pigments.
2. (Previously Presented) Surface-modified effect pigments according to Claim 1, wherein the polymer sheath has layer thicknesses of 2 – 500 nm.
3. (Previously Presented) Surface-modified effect pigments according to Claim 1, wherein the LCST polymer is a polyalkylene oxide compound, olefinically modified PEO-PPO copolymers, polymethyl vinyl ether, poly-N-vinylcaprolactam, ethyl(hydroxyethyl)cellulose, poly(N-isopropylacrylamide) or polysiloxane, or a mixture thereof.
4. (Previously Presented) Surface-modified effect pigments according to Claim 1, wherein the UCST polymer is a polystyrene, polystyrene copolymers or polyethylene oxide copolymers, or a mixture thereof.
5. (Previously Presented) Surface-modified effect pigments according to Claim 1, wherein the LCST polymer is a polysiloxane modified with olefinic groups.
6. (Previously Presented) Surface-modified effect pigments according to Claim 1, wherein the polymer sheath additionally comprises one or more nanoparticles, polymerisable monomers, plasticisers, antioxidants, carbon-black particles, microtitanium or a mixture thereof.
7. (Previously Presented) Surface-modified effect pigments according to

Claim 6, wherein the polymer sheath comprises 0.001 to 150% by weight of one or more additives, based on the polymer.

8. (Cancelled)

9. (Currently Amended) Surface-modified effect pigments according to Claim 1 [[8]], wherein the effect pigments are based on natural or synthetic mica, Al_2O_3 flakes, TiO_2 flakes, SiO_2 flakes, Fe_2O_3 flakes, glass flakes, ceramic flakes or graphite flakes.

10. (Previously Presented) A process for preparing surface-modified effect pigments according to Claim 1, wherein the LCST and/or UCST polymer is applied to the pigment surface by precipitation in water and/or an organic solvent and is irreversibly immobilized.

11. (Previously Presented) A process according to Claim 10, wherein one or more additives are added to the polymer.

12. (Previously Presented) A surface coating, water-borne coating, powder coating, paint, printing ink, security printing ink, plastic article, concrete, cosmetic composition, agricultural sheeting, tarpaulin, laser marking on a paper or plastic article, pigment composition or dry preparation, comprising surface-modified effect pigments according to Claim 1.

13. (Previously Presented) A composition comprising surface-modified effect pigments according to Claim 1.

14. (Withdrawn) A method for light protection or corrosion protection comprising applying surface-modified effect pigments according to Claim 1 to an article that is to be protected from light or corrosion.

15. (Previously Presented) Surface-modified effect pigments according to Claim 1, which are sheathed with one or more layers of immobilised UCST polymer.

16. (New) Surface-modified effect pigments based on flake-form substrates, which are sheathed with one or more layers of immobilised LCST and/or UCST polymer, wherein said surface-modified effect pigments based on flake-form substrates are holographic pigments, pearlescent pigments, interference pigments, multilayered pigments, metal-effect pigments, goniochromatic pigments and/or BiOCl pigments, which surface-modified effect pigments are prepared by applying the LCST and/or UCST polymer to the pigment surface by precipitation by controlling the temperature in water and/or in an organic solvent followed by irreversibly immobilizing the LCST and/or UCST polymer on the surface of the pigment.

17. (New) Surface-modified effect pigments according to claim 16, where the immobilization of the LCST and/or UCST polymer on the surface of the pigment is achieved by the cross-linking of the polymer.

18. (New) Surface-modified effect pigments based on flake-form substrates, which are sheathed with one or more layers of immobilised LCST and/or UCST polymer such that the LCST and/or UCST polymer does not form a chemical bond with the effect pigments, wherein said surface-modified effect pigments based on flake-form substrates are holographic pigments, pearlescent pigments, interference pigments, multilayered pigments, metal-effect pigments, goniochromatic pigments and/or BiOCl pigments.